


## Electra® technical specifications

description

performance

Characteristics	Standards	Units	Electra®
Description			Dissipative anti-static flooring
General performance	BS EN ISO 10874: 2012	Class	34 - 43
	BS EN 649 : 2011	Group	P
Usage			Heavy foot traffic
Overall thickness	EN 428	mm	2.00
Thickness of wear layer	EN 429, ASTM F410	mm	1.00
Weight	EN 430	g/m <sup>2</sup>	3500
Sheet size	EN 426	m (width)	2
		m (length)	15 / 20
		m <sup>2</sup> (surface area)	30 / 40
Tile size	EN 427	mm x mm	300 x 300
			500 x 500
			610 x 610
Abrasion resistance	EN 660 -2	Group	P
	EN 660 -2	Volume loss mm <sup>3</sup>	< 4
	ASTM D3389 (Weight loss / 1000 cycles)	g	< 0.40
Residual indentation	EN 433	mm	~ 0.03 (≤ 0.10)
	ASTM F970 (static load)	psi	800
	ASTM F1914	inches	Avg. 0.001
Slip resistance	DIN 51130		R 10
	EN 13893 ASTM D2047	Coefficient of friction	DS (> 0.30) Pass (0.70 avg)
Dimensional stability	EN 434	%	≤ 0.40
Flexibility	EN 435	mm	< 20
	ASTM F137		Pass
Castor chair test	EN 425	Type of use	Continuous
Sound insulation	EN ISO 717-2	ΔLw = dB	4
Reaction to fire	EN ISO 9239-1: 2010	kW/m <sup>2</sup>	≥ 8
	EN ISO 11925-2 : 2010		Pass
	EN 13501-1:2007+A1: 2009	Class	Bfl - S1
	ASTM E648-06	Type	1
Static electrical propensity	EN 1815	kV	< 2.0
Electrical resistance	EN 1081	Ω	< 10 <sup>9</sup> (Anti-static)
Thermal resistance	ISO 8302 (EN 12664)	m <sup>2</sup> k/W	< 0.00809
	ASTM 1514		Pass
Smoke density	ASTM E 662-05	Dm	< 450
Colour fastness to light	EN ISO 105 - B02	Degrees	≥ 6
Walking resonance	NF XPS 31 074	dB	4
Stain & chemical resistance	BS EN ISO 26987 : 2012	Index	0 (Excellent resistance)
	ASTM F925		Pass
Fungi & bacteria resistance	(E1) PCP	%	NA
	ASTM G - 21		Does not favour growth
Clean rooms	ASTM D3273		Pass
	ASTM F51/68	Class	A, non shedding
Maritime usage	IMO RES A 653 (16)		Annex 1 Part 2 (Smoke & Toxicity)
	IMO MSC 61 (67)		Part 5 (Spread of Flame) and Annexure 2
	US Coast Guard Approved		(Surface Flammability / Heat Release)
	Marine Equipment Directive		1121 



3mm thickness available to special order.

The above data is valid at the time of print. For more details regarding technical specifications, handling and installation, please contact Responsive Industries Ltd.