

Superior®

Heterogeneous Semi Contract



Characteristics	Standards	Units	Superior®
Type of floor covering	EN ISO 10582	Type 1 - Binder Content	Heterogeneous Semi Contract
General performance	EN ISO 10874 - EN 685	Classification	21 : Moderate / Light
Special Treatment			PU Treatment
Overall thickness	ISO 24346 - EN 428	mm	1.00
Thickness of wear layer	ISO 24340 - EN 429 ASTM F410	mm	0.10
Weight	ISO 23997 - EN 430	g/m ²	1600 ± 50
Sheet size	ISO 24341 - EN 426	m (Width)	2
		l (length)	20
		m ² (surface area)	40m ²
Abrasion resistance	EN 660 - 2	Group	T (Volume loss < 2mm ³)
Castor chair test	ISO 4918 - EN 425	Type of use	Continuous
Slip resistance	DIN 51130	Ramp test	R9
Dimensional stability	ISO 23999 - EN 434	%	+/- 0.40
Flexibility	ISO 24344 - EN 435	20mm mandrel	No cracking
Residual indentation	ISO 24343 - 1 - EN 433	mm	≤ 0.10
Colour fastness to light	EN ISO 105 B02	Degrees	≥ 6
Static electrical propensity	EN 1815	kV	< 2.0
Reaction to fire	EN ISO 13501 - 1	Class	Bfl - S1

